

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently amended) A glass comprising:

a base glass portion comprising:

SiO ₂	at least 67 %
Na ₂ O	10 to 20%
CaO	5 to 15%
MgO	0 to 8%
Al ₂ O ₃	0 to 5%
K ₂ O	0 to 5%

a colorant portion comprising:

total iron (expressed Fe ₂ O ₃):	0.01 to 0.20% <u>0.04 to 0.10%</u>
cobalt oxide:	0.1 to 15 ppm
chromium oxide:	0 to 10 ppm
titanium oxide:	0 to 0.5%
glass redox:	<= 0.10
%FeO:	0.0001 to 0.05%

wherein the glass has a visible transmission of at least about 85%, and wherein the glass contains 0% cerium oxide.

2. (Currently amended) The glass of claim 1, wherein the glass further comprises ~~from 0.005 to 1.0% cerium oxide,~~ and from 0 to 0.2 % titanium oxide.

3. (Original) The glass of claim 1, wherein the glass has a visible transmission of at least 88%.

4. (Original) The glass of claim 1, wherein the glass has a visible transmission of at least 90%, and a UV% transmission of no greater than about 75%.

5. (Currently amended) The glass of claim 1, wherein the colorant portion comprises:

~~total iron (expressed Fe_2O_3): 0.01 to 0.15%~~
cobalt oxide: 0.3 to 10 ppm
glass redox: ≤ 0.08 .
~~%FeO: 0.0001 to 0.01%.~~

6. (Currently amended) The glass of claim 1, wherein the colorant portion comprises:

~~total iron (expressed Fe_2O_3): 0.02 to 0.10%~~
cobalt oxide: 0.5 to 5 ppm
glass redox: ≤ 0.08 .
~~%FeO: 0.0001 to 0.008%.~~

7. (Currently amended) The glass of claim 1, wherein the colorant portion comprises:

~~total iron (expressed Fe_2O_3): 0.02 to 0.08%~~
cobalt oxide: 0.3 to 5 ppm
glass redox: ≤ 0.05
~~%FeO: 0.0001 to 0.01%~~
titanium oxide: 0 to 0.2%.

8. (Original) The glass of claim 1, wherein the glass has a UV% transmission no greater than about 75%.

9. (Original) The glass of claim 1, wherein the glass has a UV% transmission no greater than about 72%.

10. (Canceled)

11. (Original) The glass of claim 1, wherein the glass is colored as follows:

a* -1 to +1
b* -1 to +1.

12. (Currently amended) A glass comprising:

a base glass portion comprising:

SiO ₂	at least 67%
Na ₂ O	10 to 20%
CaO	5 to 15%
MgO	0 to 8%
Al ₂ O ₃	0 to 5%
K ₂ O	0 to 5%

a colorant portion consisting essentially of:

total iron (expressed Fe ₂ O ₃):	0.01 to 0.20% <u>0.04 to 0.10%</u>
cobalt oxide:	0.1 to 15 ppm
chromium oxide:	0 to 10 ppm
titanium oxide:	0 to 0.5%

wherein the glass has a visible transmission of at least about 85%, a glass redox of no greater than 0.10, and a %FeO of from ~~0.0001 to 0.05%~~ 0% cerium oxide.

13. (Canceled)

14. (Original) The glass of claim 12, wherein the glass has a visible transmission of at least 88%.

15. (Original) The glass of claim 12, wherein the glass has a visible transmission of at least 90%, and a UV% transmission of no greater than about 75%.

16. (Currently amended) The glass of claim 12, ~~wherein the colorant portion consists essentially of: total iron (expressed Fe₂O₃): 0.01 to 0.15% cobalt oxide: 0.3 to 10 ppm chromium oxide: 0 to 10 ppm titanium oxide: 0 to 0.2%~~ wherein the glass has a glass redox of no greater than 0.08, and a %FeO of from ~~0.0001 to 0.01%~~.

17. (Canceled)

18. (Original) The glass of claim 12, wherein the glass is colored as follows:

a* -1 to +1
b* -1 to +1.

19. (Currently amended) A glass comprising:

total iron (expressed Fe_2O_3): ~~0.01 to 0.15%~~ 0.04 to 0.10%
cobalt oxide: 0.1 to 15 ppm
chromium oxide: 0 to 10 ppm
titanium oxide: 0 to 0.5%
glass redox: ≤ 0.10
~~%FeO: 0.0001 to 0.05%~~

wherein the glass has a visible transmission of at least about 85% and contains 0% cerium oxide.

20. (Original) The glass of claim 19, wherein the glass is colored as follows:

a* -1 to +1
b* -1 to +1.

21. (Original) The glass of claim 19, wherein the glass is colored as follows:

a* -0.5 to +0.5
b* -0.5 to +0.5.

22. (Currently amended) The glass of claim 19, comprising:

~~total iron (expressed Fe_2O_3): 0.01 to 0.15%~~
cobalt oxide: 0.3 to 10 ppm
glass redox: ≤ 0.08 .
~~%FeO: 0.0001 to 0.01%.~~

23. (Currently amended) The glass of claim 19, comprising:

~~total iron (expressed Fe₂O₃): 0.02 to 0.10%~~
cobalt oxide: 0.5 to 5 ppm
glass redox: ≤ 0.08.
~~%FeO: 0.001 to 0.008%.~~

24. (Canceled)

25. (Original) The glass of claim 19, wherein the glass has a visible transmission of at least 88%.

26. (Original) The glass of claim 19, wherein the glass has a visible transmission of at least 90%, and a UV% transmission of no greater than about 75%.

27-34. (Canceled)

35. (Currently amended) A glass comprising a base portion, and a colorant portion consisting essentially of:

total iron (expressed Fe₂O₃): ~~0.01 to 0.20%~~ 0.04 to 0.10%
cobalt oxide: 0.1 to 15 ppm
chromium oxide: 0 to 10 ppm
titanium oxide: 0 to 0.5%

wherein the glass has a visible transmission of at least about 85%, 0% cerium oxide, and a glass redox of no greater than 0.12.

36. (Original) The glass of claim 35, wherein the glass is colored as follows:

a* -1 to +1
b* -1 to +1.

37. (Original) The glass of claim 35, wherein the glass is colored as follows:

a*	-0.5 to +0.5
b*	-0.5 to +0.5.

38. (Currently amended) The glass of claim 35, ~~wherein the colorant portion consists essentially of: total iron (expressed Fe_2O_3): 0.02 to 0.10% cobalt oxide: 0.3 to 5 ppm chromium oxide: 0 to 5 ppm titanium oxide: 0 to 0.2%~~ wherein the glass has a glass redox no greater than 0.05.

39. (Currently amended) The glass of claim 35, wherein the glass has ~~further comprising from 0.005 to 1.0% cerium oxide, and~~ a visible transmission of at least 88%.